

Product Data Sheet

CoatForce® CF50

Engineered mineral fibre (Note Q)



lapinus@lapinusfibres.com
www.lapinusfibres.com


CoatForce® CF50 is a high quality engineered mineral fibre. Its fibre length results in an excellent dispersion in various matrix materials e.g. water- and solvent based resins, bitumen. CoatForce® CF50 gives excellent mechanical properties to various paint and coating systems.

Chemical Analysis


All CoatForce® products are worldwide exonerated from classification as a carcinogen.

	Min.	Max.
SiO ₂	37 %wt	42 %wt
Al ₂ O ₃	18 %wt	23 %wt
CaO+MgO	34 %wt	39 %wt
FeO	0 %wt	1 %wt
K ₂ O+Na ₂ O		3 %wt
Others		3 %wt

Typical average fibre diameter



Typical average fibre length



ADVANTAGES OF COATFORCE® CF50

- CoatForce® CF50 shows in various applications added values in improvement of mechanical properties and rheological behaviour.
- CoatForce® CF50 has an off-white colour and very low shot content.
- CoatForce® CF50 is worldwide safe to use with respect to Health and Safety regulations.

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material	Norm. Max. N > 125 µm 0.1%wt 0.2%wt	TV 316
Fibre Length	500 ± 150 microns	TV 305
Ignition Loss	max. 0.3 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 7 micron	TV 165
Fibre diameter (num. av.)	approx. 5 micron	TV 165
Specific surface area	approx. 0.20 m ² /g	TV 165
Hardness	6 Moh	
Melting Point	> 700 °C	Furnace, Visual
Specific Density	2.71 ± 0.1 g/cm ³	
Colour	off-white	Visual
Oil absorption	approx. 20 g/100 g	ASTM D281

Author: E. Huynen
Issue: July 2008 (03)

Replaces Issue: March 2006 (02)
ISO 9001 LF007.F08

"The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose".