

Product Data Sheet



Rockbrake® RB260–Roxul® 1000

Engineered mineral fibre for application in friction materials

lapinus@lapinusfibres.com
www.lapinusfibres.com

Rockbrake® RB260–Roxul® 1000 is a high quality engineered mineral fibre. Rockbrake® RB260–Roxul® 1000 is a relatively long fibre developed for use in wet mixing processes. The percentage of non-fibrous material > 125 microns is with a maximum of 0.2% very low.


Roxul®1000 chemistry =biosoluble chemistry

All Roxul®1000 products are worldwide exonerated from classification as a carcinogen.


Chemical Analysis

	Min.	Max.
SiO ₂	38 %wt	43 %wt
Al ₂ O ₃	18 %wt	23 %wt
CaO+MgO	23 %wt	28 %wt
FeO	4.5 %wt	8 %wt
K ₂ O+Na ₂ O		4.5 %wt
Others		6 %wt

Typical average fibre diameter



Typical average fibre length



ADVANTAGES OF ROCKBRAKE® RB260–ROXUL® 1000:

- Rockbrake® RB260–Roxul® 1000 gives formulators the opportunity to decrease the use of other fibres in the matrix (aramid, steel, glass, ceramic, copper, brass), resulting in significant cost savings on a price per volume base.
- Rockbrake® RB260–Roxul® 1000 is consistent in quality in terms of:
 - chemical composition
 - purity
 - fibre length

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material	Norm. Max. N > 125 µm 0.08%wt 0.2%wt	TV 316
Fibre Length	300 ± 50 micron	TV 305
Ignition Loss	max. 0.3 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 9.0 micron	TV 165
Fibre diameter (num. av.)	approx. 5.5 micron	TV 165
Specific surface area	approx. 0.20 m ² /g	TV 165
Hardness	6 Moh	
Melting Point	> 1000 °C	Furnace, Visual
Specific Density	2.75 ± 0.15 g/cm ³	
Colour	Grey/Green	Visual

Author: E. Huynen (ADC)
Issue: September 2008 (03)

Replaces Issue: July 2004 (02)
ISO 9001 LF007.F08