

Product Data Sheet



Rockseal® RS400ELS–Roxul® 1000

Premium quality engineered mineral fibre (Note Q) for application in rubber materials

lapinus@lapinusfibres.com
www.lapinusfibres.com

Rockseal® RS400ELS–Roxul®1000 is a very short easy to disperse fibre with an Extreme Low Shot content.


Roxul®1000 chemistry =biosoluble chemistry

All Roxul®1000 products are worldwide exonerated from classification as a carcinogen.


Chemical Analysis

	Min.	Max.
SiO ₂	38 %wt	43 %wt
Al ₂ O ₃	18 %wt	23 %wt
CaO+MgO	23 %wt	28 %wt
FeO	4.5 %wt	8 %wt
K ₂ O+Na ₂ O		4.5 %wt
Others		6 %wt

Typical average fibre diameter



Typical average fibre length



FIELD OF APPLICATION

- Rockseal® RS400ELS–Roxul®1000 is especially designed for use in rubber products.
- Rockseal® RS400ELS–Roxul®1000 gives formulators the opportunity to incorporate high amounts of inorganic fibres resulting in improved temperature properties, better dimension stability and smooth surface.

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material	Norm. Max. N > 63 µm 0.2%wt 0.5%wt	TV 316
Fibre Length	125 ± 25 micron	TV 305
Ignition Loss	max. 0.3 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 9.0 micron	TV 165
Fibre diameter (num. av.)	approx. 5.5 micron	TV 165
Specific surface area	approx. 0.20 m ² /g	TV 165
Hardness	6 Moh	
Melting Point	> 1000 °C	Furnace, Visual
Specific Density	2.75 ± 0.15 g/cm ³	
Colour	Grey/Green	Visual

Author: E. Huynen (ADC)
Issue: September 2008 (05)

Replaces Issue: March 2005 (04)
ISO 9001 LF007.F08

"The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose".