

# Product Data Sheet



## Rockseal® RS470–Roxul®1000

High quality engineered mineral fibre for application in gasket materials

lapinus@lapinusfibres.com  
www.lapinusfibres.com

Rockseal® RS470–Roxul®1000 is a premium quality engineered mineral fibre. It is a long fibre with low shotcontent, surface treated with a surfactant for excellent dispersion in water.


### Roxul®1000 chemistry =biosoluble chemistry

All Roxul®1000 products are worldwide exonerated from classification as a carcinogen.


### Chemical Analysis

	Min.	Max.
SiO <sub>2</sub>	38 %wt	43 %wt
Al <sub>2</sub> O <sub>3</sub>	18 %wt	23 %wt
CaO+MgO	23 %wt	28 %wt
FeO	4.5 %wt	8 %wt
K <sub>2</sub> O+Na <sub>2</sub> O		4.5 %wt
Others		6 %wt

Typical average fibre diameter



Typical average fibre length



### FIELD OF APPLICATION

- Rockseal® RS470–Roxul®1000 is designed for use in wet (paper) process. The inorganic fibres improve green strength and drainage properties of the paper.
- The extreme low shot level ensures a smooth surface of the paper. Incorporation of high levels of inorganic fibres improves heat resistance and dimensional stability of the paper.

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material	Norm. Max. N > 125 µm 0.1%wt 0.2%wt	TV 316
Fibre Length	650 ± 150 micron	TV 305
Ignition Loss	max. 0.3 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 9.0 micron	TV 165
Fibre diameter ( num. av.)	approx. 5.5 micron	TV 165
Specific surface area	approx. 0.20 m <sup>2</sup> /g	TV 165
Hardness	6 Moh	
Melting Point	> 1000 °C	Furnace, Visual
Specific Density	2.75 ± 0.15 g/cm <sup>3</sup>	
Colour	Grey/Green	Visual

Author: E. Huynen (ADC)  
Issue: September 2008 (03)

Replaces Issue: January 2004 (02)  
ISO 9001 LF007.F08

"The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose".