

# Product Data Sheet



## Rockseal® RS475–Roxul® 1000

High quality engineered mineral fibre for application in gasket materials

lapinus@lapinusfibres.com  
www.lapinusfibres.com

Rockseal® RS475–Roxul® 1000 is a premium quality engineered mineral fibre. It is a medium long fibre with extreme low shotcontent, surface treated with a surfactant for excellent dispersion in water.


### Roxul®1000 chemistry =biosoluble chemistry

All Roxul®1000 products are worldwide exonerated from classification as a carcinogen.


### Chemical Analysis

	Min.	Max.
SiO <sub>2</sub>	38 %wt	43 %wt
Al <sub>2</sub> O <sub>3</sub>	18 %wt	23 %wt
CaO+MgO	23 %wt	28 %wt
FeO	4.5 %wt	8 %wt
K <sub>2</sub> O+Na <sub>2</sub> O		4.5 %wt
Others		6 %wt

Typical average fibre diameter



Typical average fibre length



### FIELD OF APPLICATION

- Rockseal® RS475–Roxul® 1000 is designed for use in wet (paper) process. The inorganic fibres improve green strength and drainage properties of the paper.
- The extreme low shot level ensures a smooth surface of the paper.
- Incorporation of high levels of inorganic fibres improves heat resistance and dimensional stability of the paper.

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material	Norm. Max. N > 125 µm 0.1%wt 0.2%wt	TV 316
Fibre Length	500 ± 150 micron	TV 305
Ignition Loss	max. 0.3 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 9.0 micron	TV 165
Fibre diameter ( num. av.)	approx. 5.5 micron	TV 165
Specific surface area	approx. 0.20 m <sup>2</sup> /g	TV 165
Hardness	6 Moh	
Melting Point	> 1000 °C	Furnace, Visual
Specific Density	2.75 ± 0.15 g/cm <sup>3</sup>	
Colour	Grey/Green	Visual

Author: E. Huynen (ADC)  
Issue: September 2008 (04)

Replaces Issue: December 2004 (03)  
ISO 9001 LF007.F08