

Product Data Sheet



Rockseal® RS480–Roxul® 1000

Engineered mineral fibre (Note Q) for application in gasket materials

lapinus@lapinusfibres.com
www.lapinusfibres.com

Rockseal® RS480–Roxul®1000 is a low cost, good dispersable fibre.


Roxul®1000 chemistry =biosoluble chemistry

All Roxul®1000 products are worldwide exonerated from classification as a carcinogen.


Chemical Analysis

	Min.	Max.
SiO ₂	38 %wt	43 %wt
Al ₂ O ₃	18 %wt	23 %wt
CaO+MgO	23 %wt	28 %wt
FeO	4.5 %wt	8 %wt
K ₂ O+Na ₂ O		4.5 %wt
Others		6 %wt

Typical average fibre diameter



Typical average fibre length



FIELD OF APPLICATION

- Rockseal® RS480–Roxul®1000 is designed for use in compressed sheets.
- It is possible to incorporate high amounts of these inorganic fibres and at the same time reduce the amount of (expensive) organic fibres, resulting in a gasket with improved hot compression set values and lower material costs.

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material	Norm. Max. N > 125 µm 0.6%wt 1.0%wt	TV 316
Fibre Length	200 ± 50 micron	TV 305
Ignition Loss	max. 0.3 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 9.0 micron	TV 165
Fibre diameter (num. av.)	approx. 5.5 micron	TV 165
Specific surface area	approx. 0.20 m ² /g	TV 165
Hardness	6 Moh	
Melting Point	> 1000 °C	Furnace, Visual
Specific Density	2.75 ± 0.15 g/cm ³	
Colour	Grey/Green	Visual

Author: E. Huynen (ADC)
Issue: September 2008 (03)

Replaces Issue: January 2004 (02)
ISO 9001 LF007.F08