

Product Data Sheet



Lapinus® 60046-2-Spinrock

Mineral fibre (Note Q)

lapinus@lapinusfibres.com
www.lapinusfibres.com


Lapinus® 60046-2-Spinrock is an uncleaned, white, granulated mineral fibre with a large flock size (correlating to an estimated fibre length of approx. 4000 Microns) and a high fibre content. The product shows excellent dispersion and mechanical properties in spray applications due to an optimum amount of lubricant. The consistency of the flock size gives a consistent quality in fire protective spray applications.

Chemical Analysis

All Lapinus® Granulate products are worldwide exonerated from classification as a carcinogen.

	Min.	Max.
SiO ₂	37 %wt	42 %wt
Al ₂ O ₃	18 %wt	23 %wt
CaO+MgO	34 %wt	39 %wt
FeO	0 %wt	1 %wt
K ₂ O+Na ₂ O		3 %wt
Others		3 %wt

Typical average fibre diameter



ADVANTAGES OF LAPINUS® 60046-2-SPINROCK

- Lapinus® 60046-2-Spinrock is consistent in terms of:
 - thermal properties
 - bulk properties
 - flock size distribution
 - stable white colour
 - chemical composition
- Reliable supply, excellent availability, consistent quality (ISO 9001)

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material*	Norm. Max. N > 250 µm 7.7%wt 10.5%wt	TV 701
Ignition Loss	max. 0.5 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 7.0 micron	TV 165
Fibre diameter (num. av.)	approx. 5.0 micron	TV 165
Specific surface area	approx. 0.25 m ² /g	TV 165
Hardness	6 Moh	
Melting Point	> 700 °C	Furnace, Visual
Specific Density	2.75 ± 0.15 g/cm ³	
Colour	off-white	Visual

* Please note that the occurrence of large non-fibrous particles is inherent to the production process and these may be occasionally present in the product.

Author: E. Huynen (ADC)
Issue: August 2008 (03)

Replaces Issue: August 2005 (02)
ISO 9001 LF007.F08

"The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose".