

Product Data Sheet



Lapinus® 706N2-Roxul® 1000

Mineral Fibre (Note Q)

lapinus@lapinusfibres.com
www.lapinusfibres.com

Lapinus® 706N2-Roxul®1000 is an uncleaned granulated mineral fibre with a medium flocksize (correlating to an estimated fibre length of approx. 3000 microns). The high fibre content allows a lower wool use in wet processes. The consistency of the flocksize gives a consistent drainage in wet processes.


Roxul®1000 chemistry =biosoluble chemistry

All Roxul®1000 products are worldwide exonerated from classification as a carcinogen.

Chemical Analysis

	Min.	Max.
SiO ₂	38 %wt	43 %wt
Al ₂ O ₃	18 %wt	23 %wt
CaO+MgO	23 %wt	28 %wt
FeO	4.5 %wt	8 %wt
K ₂ O+Na ₂ O		4.5 %wt
Others		6 %wt

Typical average fibre diameter



ADVANTAGES OF LAPINUS® 706N2-ROXUL®1000:

- Lapinus® 706N2-Roxul®1000 is consistent in terms of:
 - chemical composition
 - thermal properties
 - flocksize distribution
 - bulk and drainage properties
- Reliable supply, excellent availability, consistent quality (ISO 9001)

Parameter	Average/Tolerance	Testmethod												
Non-Fibrous Material*	<table border="1"> <thead> <tr> <th></th> <th>Norm.</th> <th>Max.</th> </tr> </thead> <tbody> <tr> <td>N > 600 µm</td> <td>0.7%wt</td> <td>1.2%wt</td> </tr> <tr> <td>N > 250 µm</td> <td>7.7%wt</td> <td>10.5%wt</td> </tr> <tr> <td>N > 63 µm</td> <td>33.1%wt</td> <td>38.0%wt</td> </tr> </tbody> </table>		Norm.	Max.	N > 600 µm	0.7%wt	1.2%wt	N > 250 µm	7.7%wt	10.5%wt	N > 63 µm	33.1%wt	38.0%wt	TV 701
	Norm.	Max.												
N > 600 µm	0.7%wt	1.2%wt												
N > 250 µm	7.7%wt	10.5%wt												
N > 63 µm	33.1%wt	38.0%wt												
Ignition Loss	max. 0.5 %wt	TV 302												
Moisture Content	max. 0.1 %wt	TV 302												
Fibre diameter (mass wt. av.)	approx. 9.0 micron	TV165												
Fibre diameter (num. av.)	approx. 5.5 micron	TV 165												
Specific surface area	approx. 0.20 m ² /g	TV 165												
Hardness	6 Moh													
Melting Point	> 1000 °C	Furnace, Visual												
Specific Density	2.75 ± 0.15 g/cm ³													
Colour	Grey/Green	Visual												

* Please note that the occurrence of large non-fibrous particles is inherent to the production process and these may be occasionally present in the product.

Author: E. Huynen (ADC)
Issue: July 2008 (03)

Replaces Issue: December 2003 (02)
ISO 9001 LF007.F08