

## Heracron® HP300

Para-aramid fibre for application in friction and sealing materials

Heracron® HP300 is composed of 100% para-aramide fibre.

### FIELDS OF APPLICATION

- Friction materials
- Compressed gaskets
- Technical papers

Parameter	Range	Test Method
CSF	max. 500 ml	TAPPI - 227
Specific Surface Area	4.0 ~ 6.0 m <sup>2</sup> /g	B.E.T.
Fibre Length	0.15 ~ 0.40 mm	TAPPI - 233
Moisture Content	3 ~ 7 %	TAPPI - 210

Issue: March 2012      Replaces issue: January 2010

\* "The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose."