

Product Data Sheet



Rockforce® MS615–Roxul® 1000

High quality engineered mineral fibre for application in paper like processes

lapinus@lapinusfibres.com
www.lapinusfibres.com

Rockforce® MS615–Roxul® 1000 is a very high quality engineered mineral fibre. The surface treatment results in long excellent dispersible fibres which give good reinforcing properties in various applications.


Roxul®1000 chemistry =biosoluble chemistry

All Roxul®1000 products are worldwide exonerated from classification as a carcinogen.


Chemical Analysis

	Min.	Max.
SiO ₂	38 %wt	43 %wt
Al ₂ O ₃	18 %wt	23 %wt
CaO+MgO	23 %wt	28 %wt
FeO	4.5 %wt	8 %wt
K ₂ O+Na ₂ O	4.5 %wt	4.5 %wt
Others	6 %wt	6 %wt

Typical average fibre diameter



Typical average fibre length



ADVANTAGES OF ROCKFORCE® MS615–ROXUL®1000

- Rockforce® MS615–Roxul®1000 gives formulators the opportunity to improve the drainage and green strength properties of paperlike products. The fibres are used in wet processes, resin and rubber/latex systems.
- Rockforce® MS615–Roxul®1000 is consistent in terms of:
 - chemical composition
 - surface treatment
 - fibre length
 - purity
 - thermal properties
- Rockforce® MS615–Roxul®1000 shows in various applications added values in rheology control, reinforcement, dimension stability and heat resistance

Parameter	Average/Tolerance	Testmethod
Non-Fibrous Material	Norm. Max. N > 125 µm 0.1%wt 0.2%wt	TV 316
Fibre Length	650 ± 150 micron	TV 305
Ignition Loss	max. 0.3 %wt	TV 302
Moisture Content	max. 0.1 %wt	TV 302
Fibre diameter (mass wt. av.)	approx. 9.0 micron	TV 165
Fibre diameter (num. av.)	approx. 5.5 micron	TV 165
Specific surface area	approx. 0.20 m ² /g	TV 165
Hardness	6 Moh	
Melting Point	> 1000 °C	Furnace, Visual
Specific Density	2.75 ± 0.15 g/cm ³	
Colour	Grey/Green	Visual

Author: E. Huynen (ADC)
Issue: July 2008 (04)

Replaces Issue: January 2004 (03)
ISO 9001 LF007.F08

"The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose".