

Rockseal[®] Product Range¹

Grade	Length (µm)	Max. shot (%) > 63 µm	Max. shot (%) > 125 µm	Surface treatment	Typical property	Packaging
Rockseal [®] RS400ELS-Roxul [®] 1000	125 ± 25	0.5		None	A very short easy to disperse fibre with extreme low shot content	25 kg bag 500 kg per pallet
Rockseal [®] RS440-Roxul [®] 1000	300 ± 50		1.0	S-silane	A premium quality mineral fibre with a unique surface property which gives optimum processing conditions and compatibility / reactivity with sulphur cured rubbers resulting in higher tensile strength and better immersion resistance of the product.	16 kg bag 480 kg per pallet
Rockseal [®] RS450-Roxul [®] 1000	300 ± 50		0.2	None	A premium quality engineered mineral fibre with medium fibre length and low shot content	20 kg bag 500 kg per pallet
Rockseal [®] RS470-Roxul [®] 1000	650 ± 150		0.2	Cationic surfactant	A premium quality engineered mineral fibre. It is a long fibre with low shot content, surface treated with a surfactant for excellent dispersion in water.	7 kg bag 280 kg per pallet
Rockseal [®] RS475-Roxul [®] 1000	500 ± 150		0.2	Cationic surfactant	A premium quality engineered mineral fibre. It is a medium long fibre with low shot content, surface treated with a surfactant for excellent dispersion in water.	10 kg bag 350 kg per pallet
Rockseal [®] RS480-Roxul [®] 1000	200 ± 25		1.0	None	A low cost easy to disperse fibre	20 kg bag 500 kg per pallet
Rockseal [®] RS490ELS-Roxul [®] 1000	200 ± 25	0.5		None	An easy to disperse fibre with an extreme low shot content	20 kg bag 500 kg per pallet
Rockseal [®] RS750-Roxul [®] 1000	125 ± 25		5.0	None	A low cost, easy to disperse quality fibre	25 kg bag 500 kg per pallet

¹ All Rockseal[®] products fulfill the requirements for biosolubility as defined in Note Q of EU-D 1272/2008 (CLP)