

Specialties Rockfibre Product Range¹

Grade	Length (µm)	Max. shot (%) > 125 micron	Surface treatment	Typical property	Packaging
Rockforce [®] MS600-Roxul [®] 1000	125 ± 25	1.0	None	A premium quality engineered mineral fibre with short fibre length for easy dispersion	20 kg bag 500 kg per pallet
Rockforce [®] MS603-Roxul [®] 1000	125 ± 25	0.5	None	A premium quality engineered mineral fibre with short fibre length and low shot content for easy dispersion and suitable for airless spraying	20 kg bag 500 kg per pallet
Rockforce [®] MS605-Roxul [®] 1000	300 ± 50	1.0	None	A premium quality engineered mineral fibre with medium fibre length	15 kg bag 300 kg per pallet
Rockforce [®] MS610-Roxul [®] 1000	230 ± 50	1.0	Silane	A premium quality engineered mineral fibre with medium fibre length and silane surface treatment	16 kg bag 400 kg per pallet
Rockforce [®] MS675-Roxul [®] 1000	500 ± 150	0.2	Cationic surfactant	A premium quality engineered mineral fibre. It is a medium long fibre with low shot content, surface treated with a surfactant for excellent dispersion in water.	10 kg bag 350 kg per pallet
Rockforce [®] MS730-Roxul [®] 1000	225 ± 50	30	None	Economic fibre grade with medium fibre length and a maximum shot content of 30%	20 kg bag 500 kg per pallet
Rockforce [®] MS750-Roxul [®] 1000	125 ± 25	5.0	None	A low cost easy to disperse fibre with high shot content	20 kg bag 500 kg per pallet

¹ All Rockforce[®] products fulfill the requirements for biosolubility as defined in Note Q of EU-D 1272/2008 (CLP)